

Allied Recycled Aggregates

Report Date: Oct 23, 2025

Work Order No.: 25-1032.SoilSampling.0006; ver: 1

Work Order Date: Oct 21, 2025

Reviewed by: Evan Kuhn

Soil/Aggregate Laboratory Summary

General Location: 1 x 3/4 inch crushed concrete

Logged-in by: Evan Kuhn

Photos



Allied Recycled Aggregates

Report Date: Oct 23, 2025

Work Order No.: 25-1032.SoilSampling.0006; ver: 1

Work Order Date: Oct 21, 2025

Reviewed by: Evan Kuhn

Soil/Aggregate Laboratory Summary


Specification Title: 3/4 recycled washed agg

Sampling Method: ASTM D75 / AASHTO T2 / CDOT CP30

Material Description:

Sample Location: 1 x 3/4 inch crushed concrete

Aggregate Gradation (ASTM C136 / AASHTO T27)



Coarse Gradation				Fine Gradation			
Sieve Size	Particle Size (mm)	Cumulative Passing (%)	Specified (%)	Sieve Size	Particle Size (mm)	Cumulative Passing (%)	Specified (%)
6 in	150	-	-	No. 4	4.75	1	-
5 in	125	-	-	No. 8	2.36	1	-
4 in	100	-	-	No. 10	2.00	-	-
3.5 in	90	-	-	No. 16	1.18	1	-
3 in	75	-	-	No. 20	0.85	-	-
2.5 in	63	-	-	No. 30	0.60	1	-
2 in	50	-	-	No. 40	0.425	-	-
1.5 in	37.5	-	-	No. 50	0.300	1	-
1 in	25.0	100	-	No. 60	0.250	-	-
3/4 in	19.0	70	-	No. 80	0.180	-	-
1/2 in	12.5	2	-	No. 100	0.150	1	-
3/8 in	9.5	2	-	No. 140	0.090	-	-
No. 4	4.75	1	-	No. 200	0.075	0.4	-